

TECH 28

Durable Sealing Surfaces for Corrosive Environments

Tech 28 is a composite ceramic material which adds a dimension of toughness to the composite coating line. The initial slurry is chemically modified to enhance wear characteristics when in contact with seal material. Subsequent thermochemical processing bonds precursors into the substrate resulting in a very hard, dense, and chemically inert coating.

BOND STRENGTH

TECH 28 develops a bond into the substrate through the formation of a spinel-like interphase between the ceramic coating and the metal surface. Part of the thermochemical reaction causes the substrate metal's surface atoms to migrate into the ceramic coating while some of the ceramic molecules are moving into the substrate during initial processing. Like the Tech 22 and Tech 23 coatings, **TECH 28's** bond strength to the substrate is in excess of 10,000 PSI.

DENSITY

TECH 28 is an almost totally dense (>97%) ceramic coating and, like the Tech 23 coating, has no open porosity to the substrate. Modification of the inter-granular bonding mechanism substantially increases the density of the initial coating. **TECH 28** processing completely seals off this open porosity, making the part impervious to most chemical attack.

HARDNESS

The particles in **TECH 28** coating range in hardness from 1000 to 2850 Vickers. When measured microscopically, the composite hardness is between 1000 and 1850 Vickers. In sliding wear applications, the surface wears as a result of the hardest component, chromium oxide, which has a hardness of 2850 Vickers.

RESULTS

The unique combination of particle hardness, density, chemical bonding, and lack of porosity result in a coating which is both durable and chemically resistant. A slight surface profile will allow lubrication of mechanical seals. Field use in pump sleeves and on seal surfaces prove that life expectancy of parts can be measured in years instead of weeks or months.

TECHNICAL DATA

HARDNESS	1000-1850 Vickers
OXIDATION RESISTANCE	Protects steel from oxidation to 850° C (1560° F)
CORROSION RESISTANCE	+2,000 hours in brine (no damage)
COEFFICIENT OF FRICTION	0.25 to 0.29 against polymeric fibers (adjustable) 0.10 to 0.13 against metallic (adjustable)
SURFACE FINISH	16 to 125 microinches rms (polishable)
THICKNESS	0.001" to 0.0015" (0.020 mm to 0.031 mm)
BOND STRENGTH	In excess of 10,000 psi (69 Mpa)



111 K-Tech Lane, Hot Springs, AR 71913
Phone 501 760-1696 Fax 501 760-1695